



Accepted Article

Title: Anion-dependent imidazolium-based catalysts for allylation of aniline with tunable regioselectivity

Authors: María Albert-Soriano and Isidro Pastor

This manuscript has been accepted after peer review and appears as an Accepted Article online prior to editing, proofing, and formal publication of the final Version of Record (VoR). This work is currently citable by using the Digital Object Identifier (DOI) given below. The VoR will be published online in Early View as soon as possible and may be different to this Accepted Article as a result of editing. Readers should obtain the VoR from the journal website shown below when it is published to ensure accuracy of information. The authors are responsible for the content of this Accepted Article.

To be cited as: Adv. Synth. Catal. 10.1002/adsc.202000102

Link to VoR: http://dx.doi.org/10.1002/adsc.202000102

10.1002/adsc.202000102

Anion-Dependent Imidazolium-Based Catalysts for Allylation of Aniline with Tunable Regioselectivity

María Albert-Soriano^a and Isidro M. Pastor^{a*}

 ^a Organic Chemistry Department and Instituto de Síntesis Orgánica (ISO), University of Alicante, Apdo. 99, 03080 Alicante, Spain

Fax: (+34)965903549; phone: (+34)965903728; e-mail: ipastor@ua.es

Received: ((will be filled in by the editorial staff))

Supporting information for this article is available on the WWW under http://dx.doi.org/10.1002/adsc.201########.

Abstract. Metal-free catalysts based on 1,3bis(carboxymethyl)imidazolium halides mediate the reaction between allylic alcohols and anilines, providing the corresponding N-, 2- and 4-allylaniline isomers selectively. The imidazolium counterion plays a crucial role in the outcome of the reaction. Thus, while the imidazolium chloride selectively provides the N-substituted aniline, the bromide and iodide imidazolium salts produce the 2- and 4-allylaniline isomers, respectively, with excellent selectivities. A set of complementary catalysts, which are available b simple modulation, is here presented to conduct a highly regioselective allylation reaction of anilines. Not only the catalysts are synthesized in a straightforward and easily scalable manner, but they can be recycled and used under solvent-free reaction condition, due to the favorable interactions with the reactants.

Keywords: Allylic Substitution; Heterogeneous catalysis; Imidazolium salt; Metal-free; Regioselectivity; Sustainability

Introduction

The direct allylic substitution reaction of alcohols is a straightforward strategy to afford allylic derivatives avoiding the use of coupling agents or the necessity of derivatization (e.g. acetates, phosphates, carbonates, halides),^[1] constituting an environmentally friendly alternative. When the nucleophile is an aniline derivative, three regioisomers are expected: 2allylanilines, 4-allylanilines and N-allylanilines. Most of the reported catalytic systems for the allylic substitution of alcohols with anilines lead to the predominant generation of N-allylanilines,^[2] and include metals such as palladium,^[3] gold,^[4] platinum,^[3a,5] iron,^[6] molybdenum^[7] and cobalt,^[8] amongst others. The formation of 2- and 4allylanilines has been less studied. To the best of our knowledge, the formation of 2-allylanilines (via allylic substitution of alcohols with anilines) has been Cu(OTf)₂,^[9] Re_2O_7 ,^[10] achieved using a palladacycle^[3d] and iron-based imidazolium salts (IBLAILs),^[6a] while the synthesis of 4-allylanilines has only been reported using Cu(OTf)₂.^[9] A carboxylic acid functionalized graphene oxide^[11] and a cubanetype sulfido cluster incorporating palladium and molybdenum^[12] have also been used for the synthesis 4-allylanilines, starting from *N*,*N*-dialkyl of

substituted anilines, which rules out the possibility of the aniline acting as N-nucleophile.

We have proved that the imidazolium salt 1,3bis(carboxymethyl)imidazolium chloride (bcmim-Cl), can be used as simple, efficient, regioselective and recyclable metal-free catalyst for the preparation of N_{-} allylanilines by allylic substitution of alcohols with anilines.^[13] Both the carboxyl and chloride moieties in the **bcmim-Cl** are responsible of the favorable interactions with the reactants and key in the effective preparation of quinoline and acridine derivatives.^[14] We hypothesized that different counteranions in the imidazolium salt could result in a modification in the outcome of allylic substitution reaction of alcohols with anilines. Interestingly, the replacement of the anion for other halide (i.e. bromide and iodide) allowed the selective formation of both 2- and 4allylanilines, respectively (Scheme 1). Herein, we report our finding in the development of metal-free catalytic systems for the regioselective allylic substitution of alcohols with anilines. The catalytic systems are based on 1.3bis(carboxymethyl)imidazolium halides (bcmim-X), which are ionic organic solids (IOS). These organic salts can be easily separated from the reaction mixture.



Scheme 1. Metal-free catalyzed substitution reaction of allylic alcohols with anilines: selective formation of the products by modulation of the catalytic system.

Results and Discussion

The different 1,3-bis(carboxymethyl)imidazolium halide catalysts were prepared by a simple procedure, starting from glyoxal, formaldehyde and glycine, and introducing the anion in the last step by treatment with the corresponding hydrogen halide.

The use of 1,3-bis(carboxymethyl)imidazolium chloride (bcmim-Cl) as heterogeneous catalyst in the reaction of trans-1,3-diphenylprop-2-en-1-ol (1a) and aniline (2a) at 80 °C provided, after 90 minutes, the selective formation of product 3aa in 82% conversion (Table 1, entry 1),^[13] with less than 5% of each of the other isomers being detected. Longer reaction times resulted in the formation of larger amounts of isomers 4aa and 5aa (14-18% and 14% conversion, respectively, after 6-24 h, Table 1, entries 2, 3). The temperature has also an influence in the reaction selectivity. In our previous work,^[13] we proved that both the ortho- and the para-allylanilines (i.e. 4aa and **5aa**) can be formed, in low selectivity, from the *N*-allyl substituted product 3aa by increasing the temperature and the reaction time (Table 1, entries 4 and 5), using **bcmim-Cl** as catalyst. Interestingly, the use of the imidazolium iodide analogue as catalyst (10 mol%) in our model reaction, resulted in a drastic change in the selectivity and product 5aa was formed in 77% conversion after 6 h (Table 1, entry 11). Next, we explored 1,3the reaction using bis(carboxymethyl)imidazolium bromide (bcmim-**Br**) as catalyst (Table 1, entries 6-10). Similar results to **bcmim-Cl** were obtained at low temperature (80 °C), being the N-allylated aniline **3aa** the major product of the reaction (Table 1, compare entries 1-3 with entries 6-8). However, as also observed with catalysts **bcmim-Cl** (Table 1, entry 5), increasing the temperature to 100 °C and extending the reaction time to 24 h, resulted in the selective formation of

compound **4aa** (78% conversion, Table 1, entry 10) when **bcmim-Br** was employed as catalyst. Under these conditions, **bcmim-I** gave a mixture of isomers **4aa** and **5aa** with low selectivity (ratio 1:3, Table 1, entries 13 and 14), being remarkable that isomer **3aa** was not observed with this catalyst under any reaction conditions. Consequently, the modulation of the counteranion of this simple type of catalysts allows the selective preparation of *N*-allylaniline (using **bcmim-Cl**),^[13] 2-allylaniline (using **bcmim-I**).

Table 1. (E)-1,3-diphenylprop-2-en-1-ol (1a) and aniline(2a): Effect of the catalyst



^{a)} Conversion determined by GC analysis for the compounds **3aa**, **4aa** and **5aa**.

Under the optimised reaction conditions – **bcmim-Br** (10 mol%), 100 °C, 24 h for the synthesis of 2allylanilines and **bcmim-I** (10 mol%), 80 °C, 6 h for the preparation of 4-allylanilines – the scope of the reaction was explored.

The 2-allylation reaction of trans-1,3-diphenyl-2propen-1-ol, catalysed by bcmim-Br, was carried out with different anilines (Scheme 2). Aniline, 4toluidine, 4-anisidine and 4-phenoxyaniline afforded corresponding compounds 4aa-4ad the with conversions between 60 and 93% (Scheme 2). Halogen substituted anilines provided also the expected 2-allylanilines in moderate conversions (Scheme 2, compounds 4ae and 4af). Products 4 were isolated with lower yields due to the purification process (Scheme 2, isolated yields in brackets). 3,4-Dimethoxyaniline gave the desired compound 4ag in excellent conversion and good isolated yield (Scheme 2).



Scheme 2. Evaluation of anilines for the formation of 2allyl-anilines using **bcmim-Br** as catalyst. Reaction conditions: **1** (0.5 mmol), **2** (0.5 mmol), **bcmim-Br** (10 mol%), 100 °C, 24 h. Conversion determined by ¹H-NMR analysis (in brackets, isolated yield of pure product after column chromatography).

Next, we studied the effect of substituents in aromatic rings of the 1,3-diaryl-2-propen-1-ol. As previously reported for *N*-allylanilines,^[13] non-symmetrically substituted alcohols led to the formation of two 2-allylaniline regioisomers. The regioisomers ratio was ca. 1:1 for different anilines and alcohols, regardless of the electron properties of the substituents. This agrees with the fact that 2allylanilines are formed from N-allylanilines, which are formed via a carbocation intermediate. Thus, alcohols and anilines bearing both electron-donating and electron-withdrawing groups were evaluated in the reaction leading to the formation of the corresponding 2-allylanilines in moderate conversions and yields (Scheme 3, compounds 4be, 4cd, 4cf and their corresponding regioisomers). Using 3,4dimethoxyaniline in combination with trans-1-(4chlorophenyl)-3-phenyl-2-propen-1-ol produced the expected compound 4bg in excellent conversion and yield (Scheme 3, compound 4bg and regioisomer 4bg').



Scheme 3. Evaluation of alcohols for the formation of 2allyl-anilines using **bcmim-Br** as catalyst. Reaction conditions: **1** (0.5 mmol), **2** (0.5 mmol), **bcmim-Br** (10 mol%), 100 °C, 24 h. Conversion determined by ¹H-NMR analysis (in brackets, isolated yield of pure product after column chromatography), [in square brackets, ratio of the regioisomers determined by ¹H-NMR].

Next, we explored the reaction of *trans*-1,3diphenylprop-2-en-1-ol (1a) with bcmim-I in the presence of different substituted anilines, under the optimized reaction conditions, for the synthesis of the corresponding 4-allylaniline adducts. Thus, anilines with electron-withdrawing groups afforded the corresponding 4-allylanilines in excellent conversions, compounds 5ah, 5ai, 5aj, 5ak and 5al being isolated with good yields (Scheme 4). Substituted anilines in both *ortho*-positions, such as 2-chloro-6-methylaniline and 2,6-diisopropylaniline, led to the quantitative formation of the desired compounds 5am and 5an respectively (Scheme 4) without any further purification, apart from separation of the catalyst by filtration. 2,5-Dimethylaniline afforded the desired product **5ao** in excellent conversion and yield (Scheme 4). Finally, 2-benzoylaniline gave rise to the formation of the desired product **5ap** in good conversion and yield (Scheme 4).



Scheme 4. Evaluation of anilines for the formation of 4allylanilines using **bcmim-I** as catalyst. Reaction conditions: **1** (0.5 mmol), **2** (0.5 mmol), **bcmim-I** (10 mol%), 80 °C, 6 h. Conversion determined by ¹H-NMR analysis (in brackets, isolated yield of pure product after column chromatography). ^{*a*}Pure product isolated after simple filtration.



Scheme 5. Evaluation of alcohols for the formation of 4allyl-anilines using **bcmim-I** as catalyst. Reaction conditions: **1** (0.5 mmol), **2** (0.5 mmol), **bcmim-I** (10 mol%), 80 °C, 6 h. Conversion determined by ¹H-NMk analysis (in brackets, isolated yield of pure product after column chromatography), [in square brackets, ratio of the regioisomers determined by ¹H-NMR].

Other allylic alcohol derivatives were tested in the reaction mediated by **bcmim-I** in combination with a variety of anilines. Likewise, both regioisomers (in *ca.* 1:1 ratio) were obtained with non-symmetrically substituted allylic alcohols. Alcohols bearing electron-withdrawing and donating groups in the aromatic ring

were tested in combination with different anilines, obtaining good to excellent conversions and yields in all cases (Scheme 5, compounds **5bi**, **5bo**, **5cl** and **5cm**, and their isomers). Moreover, compounds **5dj** and **5dn** were isolated in 84% and 95% yield when *trans*-1,3-di(4-chlorophenyl)-2-propen-1-ol was reacted with 2-bromoaniline and 2,6-diisopropylaniline, respectively (Scheme 5).



Figure 1. Recycling of catalysts: (a) reaction of 1a and 2g catalyzed by bcmim-Br; (b) reaction of 1a and 2m catalyzed by bcmim-I.

The recyclability of both **bcmim-Br** and **bcmim-I** catalysts was also studied. Due to their non-solubility in organic solvents, such as ethyl acetate, the same protocol employed for recycling **bcmim-Cl**^[13] was also applied here. The reaction mixture, after adding a small portion of ethyl acetate, was centrifuged to separate the catalyst; this protocol allowed the complete recovery of the catalyst (no traces were observed in the filtrate, ¹H-NMR). The recovered **bcmim-Br** catalyst could be recycled up to 3 times without loss of activity in the synthesis of compound 4ag, observing a decrease in activity in the fourth cycle (Figure 1a). Whereas, bcmim-I could be recycled up to 5 times providing full conversion in the synthesis of compound 5am, with a drastic reduction in the conversion in the sixth cycle (Figure 1b). This catalysts deactivation could be attributed to their degradation. It has been proven that the effectiveness of the catalyst depends, in part, on the halide, bearing in mind that the zwitterion [1.3bis(carboxymethyl)imidazole, bcmim] is inactive for this type of transformation.^[13] We pondered the premise that the amount of halide could decrease during the reaction and/or the work-up, the less bound the halide is to the cation, the easier the dissociation. Based on that idea, recycled **bcmim-I** (after the sixth cycle) was analyzed by ionic chromatography observing that the amount of iodide had been reduced to less than 0.1% compared with a fresh sample.

Likewise, the amount of bromide in **bcmim-Br** was reduced to less than 11%, compared with a fresh sample, after the fifth cycle. For comparison, a recycled sample of **bcmim-Cl**, which holds its activity for 15 cycles, contains 16% of the initial amount of chloride after fifteen cycles.^[13] Although, the higher robustness of the chloride salt is vindicated, it should be noted that the reactivation of all three different catalysts can be easily performed by treatment in the corresponding acid medium.



Scheme 6. Proposed mechanism for the formation of the different regioisomers by allylic substitution of alcohols with anilines.

Next, the synthetic utility of our methodology was showcased by the ease of upscaling of the reaction, allowing access to 1 g of **5am** employing only 10 mol% of **bcmim-I**. Product **5am** was isolated in quantitative yield after filtration, using ethyl acetate (4 mL) to wash the catalyst. Interestingly, this reaction presented an *E-factor* of 3.4, verifying the sustainability of the protocol.^[15]

Considering that the reactions are performed in the absence of any solvent, it is postulated that the catalysts facilitate the interactions between the reactants. The presence of the carboxy groups in the imidazolium catalyst, that enables the formation of hydrogen bonds with the reagents, is key to the catalytic process, although the interaction of the halide with the reagents appears to be also crucial.^[13-14] Thus, it can be proposed that these **bcmim-X** salts, which are ionic organic solids (IOS), establish favorable interactions by acting both as hydrogen donors and hydrogen acceptors. These interactions would favor the formation of the allylic carbocation, which is involved in the reaction mechanism, bringing the amine closer to facilitate the nucleophilic attack (Scheme 6). The measurement of the heat flow by Differential Scanning Calorimetry (DSC) of mixtures of the alcohol 1a and the different catalysts bcmim-X (X = Cl, Br, I) showed differences compared with a sample of pure alcohol 1a (Figure 2). The alcohol 1a melting thermal event is modified by the presence of the ionic organic salts (IOS), due to the favorable interactions between the components in a similar way as occurs between the components of a low transition temperature mixtures (LTTM) or deep eutectic solvents (DES).^[16] Interestingly, in the presence of both chloride and bromide salt, a similar decrease in melting temperature is observed (Figure 2b and 2c), but in the case of the iodide salt, the mixture shows a greater variation (Figure 2d). Iodide has larger ionic radius and higher polarizability than the other halides, which may facilitate interactions with alcohol **1a**. In addition, the presence of an iodide would stabilize the allyl carbocation generated during the reaction, making the nucleophilic attack selective towards the *para* position of the aromatic ring (Scheme 6). In the cases of chloride and bromide the reaction occurs, preferably, with the nitrogen acting as nucleophile, forming the N-allyl product, which can equilibrate to the more stable 2-allyl derivative (Scheme 6). Moreover, the bcmim-I catalyst, apart from being selective towards the 4-allyl product, is more effective than the chloro and bromo imidazolium salts. It was observed that the heat release in the reaction of alcohol 1a and aniline 2a in the presence of bcmim-I occurs at lower temperature compared to the reactions catalyzed by bcmim-Cl or bcmim-Br (Figure 3). Furthermore, reactions catalyzed by bcmim-Cl and bcmim-Br present similar DSC spectra, which agrees with the observed experimental results. At this point, it is worth mentioning that the selectivity in phenol tertbutylation has been reported based on the acidic sites of different catalysts,^[17] so we cannot rule out certain likeness with our case.



Figure 2. Differential Scanning Calorimetry (DSC) spectra: (a) alcohol 1a, (b) mixture of alcohol 1a and bcmim-Cl, (c) mixture of alcohol 1a and bcmim-Br and (d) mixture of alcohol 1a and bcmim-I.



Figure 3. Differential Scanning Calorimetry (DSC) spectra of the reaction mixture: alcohol **1a**, aniline (**2a**) and (a) **bcmim-Cl** (10 mol%), (b) **bcmim-Br** (10 mol%) and (c) **bcmim-I** (10 mo%).

Finally, different experiments were conducted in the presence of HCl, HBr and HI, instead of the imidazolium halides. The reactions were performed under the optimized reaction conditions for each halide. Thus, the reaction between alcohol 1a and aniline 2a, using HCl (10 mol%) at 80 °C, provided compounds **3aa** and **4aa** in 51% and 4% conversion, respectively, after 6 h (Table 2, entry 1). The reaction of **1a** and **2a**, employing HBr (10 mol%) as catalyst, afforded, after 1 h, products **3aa**, **4aa** and **5aa** in 58%, 24% and 16% conversion, respectively (Table 2, entry 2), although after 24 h, only products 4aa and 5aa were observed in 3:2 ratio (Table 2, entry 3). Similarly, the reaction catalyzed by HI (10 mol%) gave, initially, all three isomers 3aa, 4aa and 5aa (Table 2, entry 4), but provided, after 6 h, the products 4aa and 5aa in 2:3 ratio (Table 2, entry 5). The results obtained with hydrogen halides are in clear contrast with the ones obtained employing bcmim-X catalysts (Table 1). Indeed, the **bcmim-X** catalyzed reactions provide higher regioselectivities than the corresponding hydrogen halides; especially in the synthesis of the 4allylaniline isomers.

Table 2. (*E*)-1,3-diphenylprop-2-en-1-ol (**1a**) and aniline (**2a**) catalyzed by hydrogen halides



^{a)} Conversion determined by GC analysis for the compounds **3aa**, **4aa** and **5aa**.

Conclusion

To conclude, we have described three simple, effective and robust metal-free catalysts based on solid imidazolium halides, which are complementary in terms of regioselectivity for the allylic substitution of alcohols with anilines. The counterion in the 1,3 bis(carboxymethyl)imidazolium salt catalysts plays a crucial role and determines the regioselectivity of the process. Thus, the chloride catalyst selectively produces N-allylanilines, the imidazolium bromide generates 2-allylaniline isomers and the corresponding iodide catalyst mediates the selective formation of 4allylanilines. Although **bcmim-Cl** catalyst proved to be more robust than the others, with less degradation during the successive cycles, bcmim-I catalyst resulted more effective, allowing lower reaction providing unprecedented temperatures and selectivities for the synthesis of 4-allylanilines. The synthesis of all three catalysts is straightforward and easily scalable. The catalytic allylation reaction is carried out under solvent-free conditions, being the catalysts responsible for the favorable interactions in the absence of any solvent. Moreover, the catalysts are easily separated from the reaction mixture and recycled, which makes this methodology a sustainable process. These protocols represent a significant improvement compare with the previously reported ones (most of them based on metals), particularly for the 4-allylaniline isomers.

Experimental Section

Reagents and instruments. All commercially available reagents and solvents were purchased (Acros, Aldrich, Fluka) and used without further purification. Melting points were determined using a Gallenkamp capillary melting point apparatus (model MPD 350 BM 2.5) and are

uncorrected. ¹H NMR and ¹³C NMR spectra were recorded at the research technical service of the University of Alicante (SSTTI–UA), employing a Bruker AC-300 or a Bruker Advance-400.[§] Chemical shifts (δ) are given in ppm and the coupling constants (J) in Hz. The conversion of the reactions and purity of the products were determined by GC reactions and purity of the products were determined by of a analysis using an Agilent 7820A apparatus, equipped with a flame ionization detector and a Phenomenex ZB-5MS column (5% PH-ME siloxane): 30 m (length), 0.25 mm (inner diameter) and 0.25 μ m (film). Low-resolution mass spectra (EI) were obtained at 70 eV with an Agilent 5973 Network spectrometer, with fragment ions *m/z* reported with relative intensities (%) in parentheses. Low-resolution HPLC with electrospray ionization (HPLC-ESI) mass spectra were recorded at the research technical service of the University of Alicante (SSTTI–UA), employing an Agilent 1100 series apparatus with the possibility of MS/MS.[§] High resolution mass spectra (IE) were recorded at the research technical service of the University of Alicante (SSTTI–UA) with an Agilent 7200 Network spectrometer (Q-TOF).[§] Ion chromatography (IC) anions were measured at the research technical service of the University of Alicante (SSTTI–UA) technical service of the University of Alicante (SSTTI–UA) with an Ion Chromatograph, with chemical suppression, conductometric, amp and Spectrophotometric UV-VIS, Metrohm, 850 detection ProfIC Acuma - MCS, with derivatization post-column reactor.[§] Differential Scanning Calorimetry (DSC) spectra were recorded at the research technical service of the University of Alicante (SSTTI–UA) with a Heat Flow Q100 TA Instruments DSC equipped with temperature modulation. [§] Infrared spectra were recorded with an FT-IR 4100 LE (JASCO, Pike Miracle ATR) spectrometer. Spectra were recorded from neat samples and results are given in cm⁻¹. Analytical TLC was performed on Merck aluminum sheets with silica gel 60 F254, 0.2 mm thick. Silica gel 60 (0.04-0.06 mm) was employed for thick. Silica gel 60 (0.04-0.06 mm) was employed for column chromatography. P/UV₂₅₄ silica gel with CaSO₄ supported on glass plates was employed for preparative TLC. Centrifugation was carried out with a Nahita Model 2610 apparatus (4000 rpm).

Synthesis of 1,3-bis(carboxymethyl)imidazole (**bcmim**).^[18] A mixture of glycine (100 mmol, 7.5 g), glyoxal (40% in water, 50 mmol, 5.7 mL) and formaldehyde (36% in water, 100 mmol, 3.9 mL) was stirred at 95 °C for 2 h. The mixture was cooled down to room temperature and the resulting brown solid was filtered, washed with cold water and dried at room temperature to afford the corresponding product as a white solid in 89% yield.

Synthesis of 1,3-bis(carboxymethyl)imidazolium halide (bcmim-X).^[18a,19] A mixture of bcmim (920 mg, 5 mmol) and concentrated HCl (37% in water, 0.9 mL, 11.0 mmol), HBr (48% in water, 0.9 mL, 16.5 mmol) or HI (57% in water, 1.2 mL, 16.5 mmol) was stirred and refluxed for 30 minutes. Then, the corresponding hydrogen halide was removed under reduced pressure and the resultant solid was filtered and washed with acetone and diethyl ether to afford bcmim-Cl and bcmim-Br as white solids in 93% and 91% yield respectively, and bcmim-I as a reddish solid in 83% yield.

General procedure for the synthesis of 2-allylanilines (4). The corresponding allylic alcohol (1, 0.5 mmol), the corresponding aniline (2, 0.5 mmol) and bcmim-Br (10 mol%, 13.3 mg) were placed in a tube provided with a stirring bar. The mixture was stirred at 100 °C for 24 h. Then, ethyl acetate (3 mL) was added, and the mixture was filtered to separate the catalyst. After evaporating the solvent under vacuum, the corresponding crude was purified by column chromatography using mixtures of hexane/ethyl acetate. In the recycling experiments, the catalyst was separated by centrifugation and washed with ethyl acetate (2×3 mL) and with diethyl ether (1×3 mL).

General procedure for the synthesis of 4-allylanilines (5). The corresponding allylic alcohol (1, 0.5 mmol), the corresponding aniline (2, 0.5 mmol) and **bcmim-I** (10 mol%, 15.6 mg) were placed in a tube provided with a stirring bar. The mixture was stirred at 80 °C for 6 h. Then, ethyl acetate (3 mL) was added, and the mixture was filtered to separate the catalyst. After evaporating the solvent under vacuum, the corresponding crude was purified by column chromatography using mixtures of hexane/ethyl acetate. In the recycling experiments, the catalyst was separated by centrifugation and washed with ethyl acetate (2×3 mL) and with diethyl ether (1×3 mL).

Acknowledgements

This work was financially supported by the University of Alicante (VIGROB-173, VIGROB-285 and VIGROB-316F1), the Spanish Ministerio de Economía y Competitividad (CTQ2015-66624-P, CTQ2017-88171-P), the Spanish Ministerio de Ciencia, Innovación y Universidades (PGC2018-096616-B-I00) and the Generalitat Valenciana (AICO/2017/007). M.A.-S. thanks the Spanish Ministerio de Educación, Cultura y Deporte for a predoctoral fellowship (FPU15/06040). We thank Dr. Beatriz Macia-Ruiz (MMU) for valued suggestions.

References

- M. Johannsen, K. A. Jorgensen, *Chem. Rev.* 1998, 98, 1689-1708.
- [2] K. Motokura, N. Nakagiri, T. Mizugaki, K. Ebitani, K. Kaneda, J. Org. Chem. 2007, 72, 6006-6015.
- [3] a) F. Ozawa, H. Okamoto, S. Kawagishi, S. Yamamoto, T. Minami, M. Yoshifuji, J. Am. Chem. Soc. 2002, 124, 10968-10969; b) S.-C. Yang, Y.-C. Hsu, K.-H. Gan, Tetrahedron 2006, 62, 3949-3958; c) Y. Wang, M. J. P. Vaismaa, A. M. Haemaelaeinen, J. E. Tois, R. Franzen, Tetrahedron: Asymmetry 2011, 22, 524-529; d) K. Chen, Y. Li, S. A. Pullarkat, P.-H. Leung, Adv. Synth. Catal. 2012, 354, 83-87; e) D. Banerjee, K. Junge, M. Beller, Angew. Chem. Int. Ed. 2014, 53, 13049-13053; f) Y Kwon, J. Jung, J. H. Kim, W.-J. Kim, S. Kim, Asian J. Org. Chem. 2017, 6, 520-526.
- [4] a) S. Guo, F. Song, Y. Liu, Synlett 2007, 964-968; b) Y. Lu, X. Fu, H. Chen, X. Du, X. Jia, Y. Liu, Adv. Synth. Catal. 2009, 351, 129-134; c) X. Giner, P. Trillo, C. Najera, J. Organomet. Chem. 2010, 696, 357-361; d) T. Ohshima, Y. Nakahara, J. Ipposhi, Y. Miyamoto, K. Mashima, Chem. Commun. 2011, 47, 8322-8324; e) K. Huang, H. Wang, L. Liu, W. Chang, J. Li, Chem. Eur. J. 2016, 22, 6458-6465; f) H. Gu, X. Sun, Y. Wang, H. Wu, P. Wu, RSC Adv. 2018, 8, 1737-1743.
- [5] T. Ohshima, Y. Miyamoto, J. Ipposhi, Y. Nakahara, M. Utsunomiya, K. Mashima, *J. Am. Chem. Soc.* 2009, 131, 14317-14328.
- [6] a) P. Trillo, I. M. Pastor, Adv. Synth. Catal. 2016, 358 2929-2939; b) P. Trillo, A. Baeza, C. Najera, ChemCatChem 2013, 5, 1538-1542; c) P. Trillo, A. Baeza, C. Najera, Eur. J. Org. Chem. 2012, 2929-2934; d) Y. Zhao, S. W. Foo, S. Saito, Angew. Chem. Int. Ed. 2011, 50, 3006-3009.
- [7] H. Yang, L. Fang, M. Zhang, C. Zhu, Eur. J. Org. Chem. 2009, 666-672.
- [8] H. Hikawa, Y. Ijichi, S. Kikkawa, I. Azumaya, Eur. J. Org. Chem. 2017, 465-468.

- [9] K. Chen, H. J. Chen, J. Wong, J. Yang, S. A. Pullarkat, *ChemCatChem* 2013, 5, 3882-3888.
- [10] R. Nallagonda, M. Rehan, P. Ghorai, J. Org. Chem. 2014, 79, 2934-2943.
- [11] M. Gómez-Martínez, A. Baeza, D. A. Alonso, *ChemCatChem* **2017**, *9*, 1032-1039.
- [12] Y. Tao, B. Wang, J. Zhao, Y. Song, L. Qu, J. Qu, J. Org. Chem. 2012, 77, 2942-2946.
- [13] M. Albert-Soriano, L. Hernández-Martínez, I. M. Pastor, ACS Sustainable Chem. Eng. 2018, 6, 14063-14070.
- [14] P. Gisbert, M. Albert-Soriano, I. M. Pastor, *Eur. J. Org. Chem.* 2019, 4928-4940.
- [15] R. A. Sheldon, Chem. Soc. Rev. 2012, 41, 1437-1451.
- [16] a) D. J. Ramón, G. Guillena, *Deep Eutectic Solvents*, Wiley-VCH, Weinheim, **2020**; b) E. Massolo, S. Palmieri, M. Benaglia, V. Capriati, F. M. Perna, *Green Chem.* **2016**, *18*, 792-797; c) M. Capua, S. Perrone, F. M. Perna, P. Vitale, L. Troisi, A. Salomone, V. Capriati, *Molecules* **2016**, *21*, 924; d) E. L. Smith, A. P. Abbott,

K. S. Ryder, *Chem. Rev.* **2014**, *114*, 11060-11082; e) I. Hawkins, S. T. Handy, *Tetrahedron* **2013**, *69*, 9200-9204; f) M. Francisco, A. van den Bruinhorts, M. C. Kroon, *Angew. Chem. Int. Ed.* **2013**, *52*; g) C. Rus, B. König, *Green Chem.* **2012**, *14*, 2969-2982.

- [17] a) A. B. Shinde, N. B. Shrigadi, S. D. Samant, *Appl. Catal. A Gen.* 2004, 276, 5-8; b) X. Nie, X. Liu, C. Song, X. Guo, J. Mol. Catal. A: Chem. 2010, 332, 145-151; c) K. S. Kanakikodi, S. R. Churipard, A. B. Halgeri, S. P. Maradur, *Microporous Mesoporous Mater.* 2019, 286, 133-140.
- [18] a) M. Albert-Soriano, P. Trillo, T. Soler, I. M. Pastor, *Eur. J. Org. Chem.* **2017**, 6375-6381; b) O. Kühl, G. Palm, *Tetrahedron: Asymmetry* **2010**, *21*, 393-397.
- [19] Z. Fei, T. J. Geldbach, R. Scopelliti, P. J. Dyson, *Inorganic Chemistry* **2006**, 45, 6331-6337.
- § For further information of the scientific equipment, see. Research Technical Services - University of Alicante, http://sstti.ua.es/en.

FULL PAPER

Anion-dependent imidazolium-based catalysts for	
allylation of aniline with tunable regioselectivity	

Adv. Synth. Catal. Year, Volume, Page – Page

María Albert-Soriano, Isidro M. Pastor*

