Contents lists available at ScienceDirect

Tetrahedron

journal homepage: www.elsevier.com/locate/tet

Transfer hydrogenation of olefins catalysed by nickel nanoparticles

Francisco Alonso^{**}, Paola Riente, Miguel Yus^{*}*Departamento de Química Orgánica, Facultad de Ciencias and Instituto de Síntesis Orgánica (ISO), Universidad de Alicante, Apdo. 99, 03080 Alicante, Spain*

ARTICLE INFO

Article history:

Received 22 September 2009

Received in revised form

14 October 2009

Accepted 15 October 2009

Available online xxx

Keywords:

Hydrogen transfer

Reduction

Olefins

Nickel nanoparticles

ABSTRACT

Nickel nanoparticles have been found to effectively catalyse the hydrogen-transfer reduction of a variety of non-functionalised and functionalised olefins using 2-propanol as the hydrogen donor. The heterogeneous process has been shown to be highly chemoselective for certain substrates, with all the corresponding alkanes being obtained in high yields. A synthesis of the natural dihydrostilbene brittonin A is also reported based on the use of nickel nanoparticles.

© 2009 Published by Elsevier Ltd.

1. Introduction

The reduction of carbon–carbon double bonds is one of the fundamental reactions in organic chemistry. For this transformation, catalytic hydrogenation, either under homogeneous¹ or heterogeneous² conditions, is generally preferred to other non-catalytic chemical methods.³ Homogeneous catalysts have exhibited high activity and selectivity with special applications in asymmetric catalysis, although they are often expensive and their separation and reuse troublesome. In recent years, however, heterogeneous catalysis has experienced an enormous progress, with the catalysts being, in some cases, even more selective than their homogeneous counterparts. Moreover, heterogeneous catalysts are easy to separate and reuse, minimising the presence of metal traces in the product, improving the handling and process control and, therefore, reducing the overall costs. At any rate, catalytic hydrogenation requires special care in the handling of hydrogen (a highly flammable and explosive gas) and, in some cases, rather expensive catalysts and high pressures are mandatory for the reaction to occur.

In this sense, the hydrogen-transfer reduction of organic compounds⁴ is an advantageous methodology since: (a) the hydrogen source is easy to handle (no gas containment or pressure vessels are necessary), (b) possible hazards are minimised, (c) the mild reaction conditions used can afford enhanced selectivity and, (d) catalytic asymmetric transfer hydrogenation can be applied in the presence

of chiral ligands. In contrast with the reduction of carbonyl compounds, the hydrogen-transfer reduction of olefins has been little studied, mainly involving noble-metal catalysts. Phosphane–ruthenium complexes can transfer hydrogen from alcohols, formic acid, and hydroaromatic compounds to olefins.⁵ Formic acid is the hydrogen donor of choice under palladium catalysis^{6a–c} (1,4-cyclohexadiene has been recently used^{6d}), whereas rhodium and iridium complexes have been rarely applied.⁷ In the above studies, a narrow substrate scope has been tested, mainly covering activated olefins.

In the search for cheaper catalytic systems, nickel appears as an alternative to the noble metals since it is about 100-fold cheaper than palladium and ruthenium, and much cheaper than rhodium and iridium (referred to their chlorides). As a recent example, clay-entrapped nickel nanoparticles have been found to efficiently catalyse the reduction of styrenes using hydrazine as the hydrogen source.⁸ On the other hand, 2-propanol is a very popular hydrogen donor since it is cheap, non-toxic, volatile, possesses good solvent properties and it is transformed into acetone, which is environmentally friendly and easy to remove from the reaction system. Despite the attractiveness of the combination Ni/i-PrOH, only two reports describe its application to the transfer hydrogenation of olefins. In the first one, Raney nickel (10–50 wt % of total substrate) was used under reflux, showing high conversions for cinnamates and cyclic olefins and low conversions for acyclic olefins.⁹ In the second report, activated metallic nickel, prepared by thermal decomposition of in situ generated nickel diisopropoxide in boiling 2-propanol, was more effective in the reduction of non-functionalised and non-activated olefins (10–30 mol % Ni, 95–100 °C).¹⁰

Due to our continued interest on active metals,¹¹ some years ago, we reported that active nickel, prepared from stoichiometric

^{*} Corresponding author. Fax: +34 965903549.

^{**} Corresponding author.

E-mail addresses: falonso@ua.es (F. Alonso), yus@ua.es (M. Yus).

Table 1
Hydrogen-transfer reduction of 1-octene in the presence of different nickel catalysts

Entry	Ni catalyst/substrate (mmol)	T (°C)	t (h)	Yield ^a (%)
1	NiNPs 1:10	76	24	0
2	NiNPs 1:5	76	3	100
3	NiNPs 1:5	20	3	70
4	Raney Ni ^b 1:5	76	8	100
5	Raney Ni ^b 1:5	20	24	0
6	Ni–Al ^b 1:5	76	24	0
7	Ni/SiO ₂ –Al ₂ O ₃ ^b 1:5	76	24	0
8	NiO ^b 1:5	76	24	0
9	None	76	24	0

^a GLC yield.^b Commercially available catalyst. **Scheme 1.**

NiCl₂·2H₂O, lithium, and a catalytic amount of an arene, can effectively reduce alkenes.¹² Later on, we introduced the catalytic hydrogenation of alkenes using the system NiCl₂(40 mol %)-Li-[naphthalene(cat.) or polymer-supported naphthalene(cat.)] and external molecular hydrogen.¹³ Alternatively, molecular hydrogen could be generated in situ from ethanol.¹⁴ More recently, we discovered that the above generated active nickel was in the form of

nanoparticles¹⁵ and that it was particularly active in hydrogen-transfer reactions,¹⁶ namely: the α -alkylation of methyl ketones with primary alcohols,^{16a,b} the transfer hydrogenation of carbonyl compounds,^{16c,d} and reductive amination of aldehydes.^{16e} We wish to present herein an improved methodology for the reduction of olefins based on the catalytic transfer hydrogenation with nickel nanoparticles and 2-propanol as hydrogen donor.

2. Results and discussion

The nickel nanoparticles (NiNPs) were initially generated from anhydrous nickel(II) chloride, lithium powder and a catalytic amount of DTBB (4,4'-di-*tert*-butylbiphenyl, 5 mol %) in THF at room temperature. A blank experiment, consisting in a standard reaction in the absence of the substrate but in the presence of the hydrogen source (i.e., NiCl₂, Li, DTBB, THF, *i*-PrOH, 76 °C, 1 h), confirmed the formation of NiNPs.¹⁷ Transmission electron microscopy (TEM) analysis revealed the presence of spherical and highly uniform nanoparticles within the range 0.75–2.88 nm (ca. 1.75±1.00 nm).^{16c} A preliminary study was carried out using 1-octene as model substrate in order to optimise the amount of catalyst and compare with other nickel catalysts (Table 1). A 1:10 NiNPs/substrate molar ratio at 76 °C was shown to be inactive (entry 1), whereas a quantitative conversion into the product *n*-octane was observed with a 1:5 NiNPs/substrate molar ratio (20 mol % Ni) (entry 2). Interestingly, the reaction occurred with the latter even at room temperature, albeit with incomplete conversion (entry 3). A series of experiments were performed with commercially available nickel catalysts. Raney nickel behaved similarly to the NiNPs but longer reaction time was needed in

Table 2
Hydrogen-transfer reduction of non-functionalised alkenes catalysed by NiNPs^a

Entry	Alkene	t (h)	Product ^b	Yield ^c (%)
1		3		>99
2		2		>99 ^d
3		2		>99
4		1		60
5		1		>99 ^d (40) ^e
6		1		>99
7		4		>99 ^d
8		2		>99
9		72		>99
10		5		>99

^a Alkene (5 mmol), NiNPs (1 mmol), 2-propanol (5 mL), 76 °C.^b All isolated products were ≥95% pure (GLC and/or ¹H NMR).^c GLC yield, unless otherwise stated.^d Isolated yield.^e Reported conversion with Raney nickel after 4 h at 80 °C.⁹

order to achieve the same conversion at 76 °C (entry 4), while the activity of the former drastically dropped at room temperature (entry 5). Other commercially available nickel catalysts, such as Ni–Al, Ni/SiO₂–Al₂O₃, or NiO, were totally inactive under the above mentioned conditions (entries 6–8). The starting alkene was also the only reaction product when the reaction was carried out in the absence of any nickel catalyst (Li, DTBB, THF, *i*-PrOH; entry 9).

The optimised reaction conditions (Scheme 1) were first applied to a variety of non-functionalised olefins (Table 2). Terminal alkenes were easily reduced to the corresponding alkanes in quantitative yield (entries 1 and 2). The same behaviour was observed for the

internal alkene *trans*-4-octene (entry 3), whereas *trans*-5-decene could not be completely reduced (entry 4). *Trans*-stilbene was readily and quantitatively transformed into 1,2-diphenylethane (entry 5). In contrast, only 40% conversion was achieved for the reaction catalysed by Raney nickel.⁹ In this case, the authors reported the formation of 1-phenyl-2-cyclohexylethane as a side product on prolonged heating (entry 5, footnote e). Longer reaction time was needed for the geminal alkene 1,1-diphenylethane (entry 7) in comparison with *trans*-stilbene and α -methylstyrene (entry 6), although the product was also obtained in excellent yield. The cyclic substrates cyclooctene, 1,5-cyclooctadiene, and 1,3-cyclooctadiene

Table 3
Hydrogen-transfer reduction of functionalised alkenes catalysed by NiNPs^a

Entry	Alkene	<i>t</i> (h)	Product ^b	Yield ^c (%)
1		2		89 ^d
2		24 ^e		>99
3		2		99 ^f
4		48		>99
5		3		>99
6		2		96
7		4		>99
8		3		90
9		72		51 (90) ^g
10		3		>99 (0) ^h
11		2		>99 (0) ^h

^a Alkene (5 mmol), NiNPs (1 mmol), 2-propanol (5 mL), 76 °C.

^b All isolated products were ≥95% pure (GLC and/or ¹H NMR).

^c Isolated yield.

^d It includes 11% of the transesterified product isopropyl heptanoate.

^e Reaction performed at room temperature.

^f It includes 22% of the transesterified product isopropyl hexanoate.

^g Conversion in parenthesis.

^h Yield obtained with Raney nickel after 24 h at 76 °C in parenthesis.

were successfully converted into cyclooctane, with the isolated diene 1,5-cyclooctadiene, a well-known ligand for Ni(0), being more reluctant to react.

We next studied the reduction of a series of functionalised olefins (Table 3). Both terminal and internal unsaturated esters were rapidly reduced to the corresponding saturated esters in high yields, including minor amounts of the isopropyl esters resulting from partial transesterification (entries 1 and 3). Interestingly, transesterification could be completely suppressed for ethyl 6-heptenoate when the reaction was performed at room temperature (entry 2). The transfer hydrogenation of 4-allyl-2-methoxyphenol was, however, rather slow, though complete conversion into the expected product was reached after prolonged heating (entry 4). The electron-rich aromatics 3,4-dimethoxystyrene and isosafrole were also nicely reduced in high isolated yields (entries 5 and 6). Good results were obtained for allylic alcohols, with either a monosubstituted or geminal carbon–carbon double bond (entries 7 and 8). In these cases, we did not observe any isomerisation to the corresponding carbonyl compounds. It is well known that transition-metal catalysts, some of which are also used in catalytic hydrogenation, can induce this type of isomerisation.¹⁸ In particular, the competition between hydrogenation and isomerisation of allylic alcohols over different supported palladium catalysts, including Pd/C, has been often described.¹⁹ It is noteworthy, that even the monoterpene (±)-linalool, which contains both a mono- and a tri-substituted carbon–carbon double bond, was transformed into the saturated tertiary alcohol 3,7-dimethyloctan-3-ol (tetrahydrolinalool) in moderate yield and longer reaction time (entry 9). Apparently, this transformation is not so trivial, with most methods showing a preferential reduction of the terminal carbon–carbon double bond.²⁰

The reduction of allyl benzyl ether and *N*-allylcyclohexylamine deserves a comment aside. In both cases, the desired products were obtained in short reaction times and quantitative yields (Table 3, entries 10 and 11). Furthermore, no deallylation products were detected despite the known ability of nickel(0) to catalyse the allyl group cleavage in ethers²¹ and amines.²² In addition, removal of the benzyl group in allyl benzyl ether by hydrogenolysis was prevented (entry 10). This result is very interesting if we take into account that benzyl ethers can undergo hydrogenolysis, under the same standard conditions used for the catalytic hydrogenation of olefins (e.g., H₂–Pd/C, EtOH).²³ In order to know whether this special behaviour was particular for the NiNPs, a short comparative study was conducted with different nickel catalysts (Scheme 2). Raney nickel did not alter the starting material, whereas Ni(*O*-*i*-Pr)₂ afforded benzyl *n*-propyl ether in moderate yield. According to the authors, in the latter case, the substrate underwent both partial hydrogenolysis and carbon–carbon double bond migration.¹⁰ Therefore, the NiNPs were shown to be superior to Raney nickel, which besides being the most universal and commercially available nickel catalyst, we must not ignore some of its inherent disadvantages, namely: (a) the difficulty in calculating the dosage (it is usually measured as a suspension rather than weighed); (b) ferromagnetic properties that preclude the use of magnetic stirring; (c) it is potentially hazardous (pyrophoric); and (d) it becomes inactive after prolonged storage, presumably because it loses hydrogen slowly.

Scheme 2. Comparative transfer hydrogenation of allyl benzyl ether with different nickel catalysts.

The versatility of the NiNPs was demonstrated in the synthesis of brittonin A, a natural dihydrostilbene isolated from *Frullania brittoniae* subsp. *truncatifolia* (*Fischerella muscicola*).²⁴ We have recently reported a novel synthesis of stilbenes, from benzyl alcohols as phosphorus ylide partners, through a one-pot Wittig-type olefination reaction promoted by nickel nanoparticles.²⁵ Resveratrol, DMU-212, and analogues have been synthesised using this methodology.²⁶ The precursor of the target molecule, dehydrobrittonin A, is a symmetrically-substituted highly polymethoxylated stilbene that could be synthesised from only one starting material (Scheme 3). Thus, 3,4,5-trimethoxybenzyl alcohol served both as the precursor of the corresponding ylide and as its partner in the Wittig-type olefination. This reaction was shown to be slower, in comparison with the homologues with less methoxy substituents, leading to the expected stilbene in moderate yield as a mixture of diastereoisomers. Final hydrogen-transfer reduction of dehydrobrittonin A, catalysed by NiNPs, furnished brittonin A in quantitative conversion after 2 h and 95% isolated yield (Scheme 3).

Scheme 3. Synthesis of the natural dihydrostilbene brittonin A.

We also studied the possibility of reutilisation of the NiNPs using *trans*-stilbene as the substrate. Thus, once the reaction was stopped, the NiNPs were decanted and the supernatant removed, followed by further addition of 2-propanol and the substrate. Table 4 shows that the NiNPs, in a 1:1 M ratio, could be reused over four consecutive cycles with a quantitative conversion into the reduced product. It was observed, however, that longer time was required in each cycle to reach a complete conversion. This progressive catalyst deactivation was more pronounced for a 1:5 NiNPs/substrate molar ratio, with an important decrease in the conversion being observed in the second cycle. The latter result

differs from that obtained in the transfer hydrogenation of carbonyl compounds, where the NiNPs could be reused over five consecutive cycles with a good performance.^{16d}

Table 4

Reutilisation of NiNPs in the hydrogen-transfer reduction of *trans*-stilbene

Run	1	2	3	4	5
Yield ^a (%)	100 (1)	100 (1.5)	100 (3)	100 (7)	16 (24)
	[100] (1)	[41] (24)	—	—	—

^a GLC yield after the specified time (in parenthesis) for a 1:1 NiNPs/substrate ratio. The results for a 1:5 NiNPs/substrate ratio are shown in brackets.

Concerning the reaction mechanism and based on deuterium labeling experiments, previously carried out for the transfer hydrogenation of carbonyl compounds with isopropanol,^{16c} a similar dihydride-type mechanism could be invoked in this case, where the two hydrogen atoms of the donor become equivalent after being transferred to the metal to give the dihydride (Scheme 4). It must be clarified that dihydride species refer in this case to those resulting from the transfer of the two hydrogen atoms of the donor to the surface of the metal.

Scheme 4. Proposed dihydride-type mechanism for the transfer hydrogenation of olefins with isopropanol catalysed by NiNPs.

3. Conclusion

We have demonstrated, for the first time, that nickel nanoparticles can effectively catalyse the heterogeneous transfer hydrogenation of olefins using 2-propanol as the hydrogen donor. A variety of non-functionalised and functionalised olefins have been reduced in high yields. The process has been shown to be highly chemoselective for substrates, which are prone to undergo isomerisation or hydrogenolysis. Moreover, the NiNPs-catalysed transfer hydrogenation, in combination with a previous NiNPs-promoted Wittig-type olefination, has been applied to the synthesis of the natural dihydrostilbene brittonin A. The transfer hydrogenation methodology presented herein is, in general, superior to others involving nickel catalysts and can be considered as an interesting alternative to other reduction methods involving noble-metal catalysts, including catalytic hydrogenation.

4. Experimental

4.1. General

THF was directly used without any purification (Acros, 99.9%). Anhydrous nickel(II) chloride (Aldrich, 98%), lithium powder (MED-ALCHEMY S. L.), and 2-propanol (Panreac, Acros, ≥99.5%) were commercially available. All the starting materials were commercially available of the best grade (Aldrich, Acros, Alfa Aesar) and were used without further purification. NMR spectra were recorded on 300 and 400 spectrometers (300 and 400 MHz for ¹H NMR, and 75 and 100 MHz for ¹³C NMR, respectively) using CDCl₃ as solvent and TMS as internal standard; chemical shifts are given in δ (ppm) and coupling constants (*J*) in Hertz. Mass spectra (EI) were obtained at 70 eV,

fragment ions in *m/z* with relative intensities (%) in parenthesis. The purity of volatile compounds and the chromatographic analyses (GLC) were determined with an instrument equipped with a flame ionisation detector and a 30 m capillary column (0.32 mm diameter, 0.25 μm film thickness), using nitrogen (2 mL/min) as carrier gas, *T*_{injector}=275 °C, *T*_{column}=60 °C (3 min) and 60–270 °C (15 °C/min); retention times (*t*_r) are given under these conditions. Thin layer chromatography was carried out on TLC plastic sheets with silica gel 60 F₂₅₄ (Merck). All products in Tables 2 and 3 were characterised by comparison of their physical and spectroscopic properties with those of commercially available samples: *n*-octane (Aldrich, 111–65–9), 1-(*n*-butyl)benzene (Aldrich, 104–51–8), *n*-decane (Aldrich, 124–18–5), 1,2-diphenylethane (Aldrich, 103–29–7), cumene (Aldrich, 98–82–8), 1,1-diphenylethane (Waterstone-technology-USA, 612–00–0), cyclooctane (Aldrich, 292–64–8), ethyl heptanoate (Aldrich, 106–30–9), ethyl hexanoate (Aldrich, 123–66–0), 2-methoxy-4-(*n*-propyl)-phenol (Aldrich, 2785–87–7), 4-ethyl-1,2-dimethoxybenzene (ACC, 5888–51–7), 5-*n*-propylbenzo[d][1,3]dioxole (3B Scientific corporation, 94–58–6), decan-3-ol (Alfa Aesar, 1565–81–7), 2-methyl-1-phenylpropan-1-ol (Aldrich, 611–69–8), 3,7-dimethyloctan-3-ol (Aldrich, 78–69–3), benzyl *n*-propyl ether (Ryan Scientific, 937–61–1), and *N*-(*n*-propyl)cyclohexanamine (Ryan Scientific, 3592–81–2). Brittonin A was characterised by comparison of its physical and spectroscopic data with those described in the literature.²⁴

4.2. General procedure for the NiNPs-catalysed transfer hydrogenation of olefins

The NiNPs suspension was freshly prepared by adding nickel(II) chloride (130 mg, 1 mmol) over a suspension of lithium (14 mg, 2 mmol) and DTBB (13 mg, 0.05 mmol) in dry THF (2 mL) at room temperature under argon. The reaction mixture, which was initially dark blue, changed to black indicating that nickel(0) nanoparticles were formed. After 10 min, *i*-PrOH (5 mL) and the corresponding alkene (5 mmol) were consecutively added. The reaction mixture was warmed up to 76 °C and monitored by GLC–MS until total or steady conversion of the starting material. The resulting suspension was diluted with diethyl ether (20 mL), filtered through a pad containing Celite and the filtrate was dried over MgSO₄. The residue obtained after removal of the solvent (15 Torr) was pure enough or was purified by column chromatography (silica gel, hexane or hexane/EtOAc) to give the corresponding pure alkane.

4.2.1. 1-*n*-Butylbenzene (Table 2, entry 2). Colourless oil; *t*_r 7.07; *R*_f 0.35 (hexane/EtOAc 95:5); δ_H 0.92 (3H, t, *J*=5.3, CH₃), 1.32–1.38 (2H, m, CH₂CH₃), 1.55–1.63 (2H, m, CH₂CH₂CH₃), 2.59 (2H, t, *J*=7.5, ArCH₂), 7.13–7.27 (5H, m, 5×ArH); δ_C 13.9 (CH₃), 22.3, 33.6, 35.6 (3×CH₂), 125.5, 128.1, 128.3 (ArCH), 142.8 (ArC); *m/z* 134 (*M*⁺, 3%), 92 (55), 91 (100), 65 (12).

4.2.2. 1,2-Diphenylethane (Table 2, entry 5). White solid; mp 51–53 °C (hexane); *t*_r 11.81; *R*_f 0.47 (hexane); δ_H 2.87 (4H, s, 2×CH₂), 7.10–7.24 (10H, m, 10×ArH); δ_C 37.8 (2×CH₂), 125.8, 128.2, 128.3 (10×ArCH), 141.6 (2×ArC); *m/z* 182 (*M*⁺, 30%), 91 (100), 65 (18).

4.2.3. 1,1-Diphenylethane (Table 2, entry 6). Colourless oil; *t*_r 11.56; *R*_f 0.50 (hexane/EtOAc 95:5); δ_H 1.59 (3H, d, *J*=7.3, CH₃), 4.09 (1H, q, *J*=7.3, CHCH₃); 7.09–7.24 (10H, m, 10×ArH); δ_C 21.8 (CH₃), 44.7 (CHCH₃), 125.9, 127.5, 128.2 (10×ArCH), 146.2 (2×ArC); *m/z* 182 (*M*⁺, 36%), 168 (14), 167 (100), 165 (32), 152 (17), 77 (10).

4.2.4. Ethyl heptanoate (Table 3, entry 2). Colourless oil; *t*_r 7.51; *R*_f 0.15 (hexane/EtOAc 95:5); δ_H 0.88 [3H, t, *J*=6.8, (CH₂)₃CH₃], 1.22–1.36 [9H, m, (CH₂)₃CH₃, OCH₂CH₃], 1.59–1.63 (2H, m, CH₂CH₂CO), 2.26 (2H, t, *J*=7.8, CH₂CH₂CO), 4.12 (2H, q, *J*=7.1, OCH₂CH₃); δ_C 13.7, 13.8 (2×CH₃), 22.2, 24.9, 28.7, 31.3, 34.4, 60.1 (6×CH₂), 173.8 (CO);

640 m/z 158 (M^+ , 1%), 115 (17), 113 (41), 101 (30), 88 (100), 85 (11), 73
641 (22), 70 (20), 61 (17), 60 (25), 55 (19).

642
643 4.2.5. *Ethyl hexanoate* (Table 3, entry 3). Colourless oil; t_r 6.24; R_f
644 0.15 (hexane/EtOAc 95:5); δ_H 0.89 (3H, t, $J=6.8$, $CH_2CH_2CH_3$), 1.22–1.36
645 [7H, m, $(CH_2)_2CH_3$, OCH_2CH_3], 1.59–1.65 (2H, m, CH_2CH_2CO), 2.23–
646 2.31 (2H, m, CH_2CO), 4.12 (2H, q, $J=7.1$, OCH_2CH_3); δ_C 14.1 ($2\times CH_3$),
647 22.2, 24.6, 31.2, 34.6, 60.0 ($5\times CH_2$), 173.8 (CO); m/z 144 (M^+ , 1%), 101
648 (27), 99 (56), 88 (100), 73 (27), 71 (25), 70 (29), 61 (19), 60 (34), 55 (23).

649
650 4.2.6. *2-Methoxy-4-(n-propyl)phenol* (Table 3, entry 4). Colourless
651 oil; t_r 10.40; R_f 0.12 (hexane/EtOAc 95:5); δ_H 0.92 (3H, t, $J=7.3$, CH_3),
652 1.54–1.64 (2H, m, CH_2CH_3), 2.49 (2H, t, $J=7.8$, $ArCH_2$), 3.80 (3H, s,
653 CH_3O), 5.01 (1H, s, OH), 6.63 (1H, s, ArH), 6.65, 6.80 (2H, d, $J=8.0$,
654 $2\times ArH$); δ_C 13.7 (CH_3), 24.5, 37.4 ($2\times CH_2$), 55.4 (CH_3O), 114.1, 120.6,
655 125.3 ($3\times ArCH$), 134.3, 143.2, 146.3 ($3\times ArC$); m/z 166 (M^+ , 23%), 137
656 (100), 122 (10).

657
658 4.2.7. *4-Ethyl-1,2-dimethoxybenzene* (Table 3, entry 5). Colourless
659 oil; t_r 9.94; R_f 0.28 (hexane/EtOAc 9:1); δ_H 1.22 (3H, t, $J=7.5$, CH_3),
660 2.59 (2H, q, $J=7.5$, CH_2), 3.83, 3.86 (6H, s, $2\times CH_3O$), 6.71–6.72 (2H,
661 m, $2\times ArH$), 6.72–6.79 (1H, m, ArH); δ_C 15.6 (CH_3), 28.2 (CH_2), 55.5,
662 55.7 ($2\times CH_3O$), 110.8, 111.0, 119.2 ($3\times ArCH$), 136.7 (ArC), 146.8,
663 148.6 ($2\times ArCO$); m/z 166 (M^+ , 61%), 164 (10), 152 (10), 151 (100), 95
664 (14), 91 (18), 79 (10), 77 (17).

665
666 4.2.8. *5-Propylbenzo[d][1,3]dioxole (dihydrosafrole)* (Table 3, entry
667 6). Yellow oil; t_r 9.75; R_f 0.40 (hexane/EtOAc 95:5); δ_H 0.92 (3H, t,
668 $J=7.4$, CH_3), 1.56 (2H, sextet, $J=7.4$, CH_2CH_3), 2.49 (2H, t, $J=7.4$,
669 $ArCH_2$), 5.87 (2H, s, CH_2O), 6.58–6.72 (3H, m, $3\times ArH$); δ_C 13.5 (CH_3),
670 24.7, 37.6, 100.5 ($3\times CH_2$), 107.9, 108.8, 121.0 ($3\times ArCH$), 136.4 (ArC),
671 145.3, 147.4 ($2\times ArCO$); m/z 164 (M^+ , 28%), 135 (100), 77 (17).

672
673 4.2.9. *Decan-3-ol* (Table 3, entry 7). Colourless oil; t_r 8.64; R_f 0.42
674 (hexane/EtOAc 9:1); δ_H 0.86–0.96 (6H, m, $2\times CH_3$), 1.03–1.55 (14H,
675 m, $7\times CH_2$), 2.37 (1H, s, OH), 3.51 (1H, quintet, $J=4.6$, CH); δ_C 7.8, 14.1
676 ($2\times CH_3$), 22.6, 23.9, 29.6, 30.0, 31.3, 31.8, 36.9 ($7\times CH_2$), 73.2 (CH);
677 m/z 140 (M^+ –18, 21%), 129 (23), 111 (20), 97 (12), 84 (11), 83 (15), 70
678 (32), 69 (100), 67 (14), 59 (92), 58 (12), 57 (38), 56 (42), 55 (78), 54
679 (10), 53 (11).

680
681 4.2.10. *2-Methyl-1-phenylpropan-1-ol* (Table 3, entry 8). Colourless
682 oil; t_r 8.84; R_f 0.16 (hexane/EtOAc 9:1); δ_H 0.76, 0.97 (6H, d, $J=6.7$,
683 $2\times CH_3$), 1.85–1.94 [1H, m, $CH(CH_3)_2$], 2.0 (1H, s, OH), 4.28 (1H, d,
684 $J=6.1$, CHO), 7.23–7.32 (5H, m, $5\times ArH$); δ_C 18.1, 18.8 ($2\times CH_3$), 35.1,
685 80.0 ($2\times CH$), 126.4, 127.1, 128.0 ($5\times ArCH$), 143.6 (ArC); m/z 150 (M^+ ,
686 3%), 132 (67), 131 (16), 118 (11), 117 (100), 116 (15), 115 (53), 107 (42),
687 105 (53), 91 (43), 79 (26), 78 (11), 77 (24), 65 (14), 63 (12), 51 (17).

688
689 4.2.11. *3,7-Dimethyloctan-3-ol* (Table 3, entry 9). Colourless oil; t_r
690 7.53; R_f 0.19 (hexane/EtOAc 9:1); δ_H 0.87–0.90 (9H, m, $3\times CH_3$), 1.16–
691 1.31 [7H, m, CH_3C , $CH_2CH_2CH(CH_3)_2$], 1.32–1.58 [5H, m,
692 $CH_2C(OH)CH_2$, $CH(CH_3)_2$], 2.04 (1H, s, OH); δ_C 8.1 (CH_3), 21.5 (CH_2),
693 22.5, 26.3 ($3\times CH_3$), 27.9 (CH), 34.1, 39.5, 41.5 ($3\times CH_2$), 72.8 (C); m/z
694 140 (M^+ –18, 31%), 111 (16), 84 (10), 83 (21), 73 (38), 71 (15), 70 (88),
695 69 (69), 67 (19), 57 (15), 56 (31), 55 (100), 53 (17).

696
697 4.2.12. *Benzyl n-propyl ether* (Table 3, entry 10). Colourless oil; t_r
698 8.20; R_f 0.14 (hexane/EtOAc 95:5); δ_H 0.93 (3H, t, $J=7.5$, CH_3), 1.58–
699 1.65 (2H, m, CH_2CH_3), 3.42 (2H, t, $J=7.3$, $CH_2CH_2CH_3$), 4.49 (2H, s,
700 $ArCH_2$), 7.24–7.26 (5H, m, $5\times ArH$); δ_C 10.3 (CH_3), 22.7, 70.9, 71.9
701 ($3\times CH_2$), 127.4, 127.5, 128.1, 128.2 ($5\times ArCH$), 138.3 (ArC); m/z 150
702 (M^+ , 2%), 92 (70), 91 (100), 79 (11), 77 (11), 65 (14).

703
704 4.2.13. *N-(n-Propyl)cyclohexanamine* (Table 3, entry 11). Yellow oil;
705 t_r 7.40; R_f 0.25 (hexane/EtOAc 9:1); δ_H 0.92 (3H, t, $J=7.3$, CH_3), 1.01–

1.89 [13H, m, $(CH_2)_5$, CH_2CH_3 , NH], 2.37–2.44 (1H, m, CH), 2.58 (2H, t,
 $J=7.3$, CH_2N); δ_C 11.8 (CH_3), 23.4, 25.0, 26.1, 33.6, 48.8 ($7\times CH_2$), 56.8
(CH); m/z 141 (M^+ , 19%), 112 (47), 98 (100), 70 (12), 56 (25), 55 (14).

4.2.14. *1,2-Bis(3,4,5-trimethoxyphenyl)ethane (brittonin A)*²⁴. White
solid; mp 142–143 °C (hexane); t_r 19.68; R_f 0.53 (hexane/EtOAc
7:3); δ_H 2.85 (4H, s, $2\times CH_2$), 3.83 (18H, s, $6\times CH_3$), 6.36 (4H, s,
 $4\times ArH$); δ_C 38.4 ($2\times CH_2$), 56.0 ($6\times CH_3$), 105.3 ($4\times ArCH$), 136.1
($2\times ArC$), 137.3, 153.0 ($6\times ArCO$); m/z 362 (M^+ , 32%), 181 (100).

Acknowledgements

This work was generously supported by the Spanish Ministerio de Educación y Ciencia (MEC; grant no. CTQ2007-65218; Consolider Ingenio 2010-CSD2007-00006). P.R. also thanks the MEC for a pre-doctoral grant.

Appendix. Supplementary data

Supplementary data associated with this article can be found, in the online version, at doi:10.1016/j.tet.2009.10.057.

References and notes

- For reviews and monographs, see: (a) Takaya, H.; Noyori, R. In *Comprehensive Organic Synthesis*; Trost, B. M., Fleming, I., Eds.; Pergamon: Oxford, 1991; Vol. 8, Chapter 3.1; (b) Chaloner, P. A.; Esteruelas, M. A.; Joo, F.; Oro, L. A. *Homogeneous Hydrogenation*; Kluwer Academic: Dordrecht, 1994; (c) Cui, X.; Burgess, K. *Chem. Rev.* **2005**, 105, 3272–3296; (d) *Catalysts for Fine Chemical Synthesis*; Roberts, S., Whittall, J., Eds.; John Wiley & Sons: New York, NY, 2007; Vol. 5, Chapter 2; (e) *Handbook of Homogeneous Hydrogenation*; de Vries, J. G., Elsevier, C. J., Eds.; Wiley-VCH: Weinheim, 2007; (f) Genet, J.-P. In *Modern Reduction Methods*; Andersson, P. G., Munslow, I. J., Eds.; Wiley-VCH: Weinheim, 2008, Chapter 1; (g) Diesen, J. S.; Andersson, P. G. In *Modern Reduction Methods*; Andersson, P. G., Munslow, I. J., Eds.; Wiley-VCH: Weinheim, 2008, Chapter 2.
- For reviews, see: (a) Siegel, S. In *Comprehensive Organic Synthesis*; Trost, B. M., Fleming, I., Eds.; Pergamon: Oxford, 1991; Vol. 8, Chapter 3.2; (b) Nishimura, S. *Handbook of Heterogeneous Catalytic Hydrogenation for Organic Synthesis*; John Wiley & Sons: New York, NY, 2001; (c) Molnar, A.; Sarkany, A.; Varga, M. *J. Mol. Catal. A: Chem.* **2001**, 173, 185–221.
- For a review, see: Pasto, D. J. In *Comprehensive Organic Synthesis*; Trost, B. M., Fleming, I., Eds.; Pergamon: Oxford, 1991; Vol. 8, Chapter 3.3.
- For reviews, see: (a) Johnstone, R. A. W.; Wilby, A. H. *Chem. Rev.* **1985**, 85, 129–170; (b) Kellogg, R. M. In *Comprehensive Organic Synthesis*; Trost, B. M., Fleming, I., Eds.; Pergamon: Oxford, 1991; Vol. 8, Chapter 1.3; (c) Bäckvall, J.-E. *J. Organomet. Chem.* **2002**, 652, 105–111.
- Kitamura, M.; Noyori, R. In *Ruthenium in Organic Synthesis*; Murahashi, S.-I., Ed.; Wiley-VCH: Weinheim, 2004; pp 31–32.
- (a) Elamin, B.; Park, J. W.; Means, G. E. *Tetrahedron Lett.* **1988**, 29, 5599–5600; (b) Basu, B.; Das, S.; Das, P.; Nanda, A. K. *Tetrahedron Lett.* **2005**, 46, 8591–8593; (c) Brunel, J. M. *Tetrahedron* **2007**, 63, 3899–3906; (d) Quinn, J. F.; Razzano, D. A.; Golden, K. C.; Gregg, B. T. *Tetrahedron Lett.* **2008**, 49, 6137–6140.
- (a) Spogliarich, R.; Tencich, A.; Kaspar, J.; Graziani, M. *J. Organomet. Chem.* **1982**, 240, 453–459; (b) Gnanamgari, D.; Moores, A.; Rajaseelan, E.; Crabtree, R. H. *Organometallics* **2007**, 26, 1226–1230.
- Dhakshinamoorthy, A.; Pitchumani, K. *Tetrahedron Lett.* **2008**, 49, 1818–1823.
- Andrews, M. J.; Pillai, C. N. *Indian J. Chem.* **1978**, 16B, 465–468.
- Boldrini, G. P.; Savoia, D.; Tagliavini, E.; Trombini, C.; Umani-Ronchi, A. *J. Org. Chem.* **1985**, 50, 3082–3086.
- For reviews, see: (a) Alonso, F.; Radivoy, G.; Yus, M. *Russ. Chem. Bull., Int. Ed.* **2003**, 52, 2563–2576; (b) Alonso, F.; Yus, M. *Chem. Soc. Rev.* **2004**, 33, 284–293; (c) Alonso, F.; Yus, M. *Pure Appl. Chem.* **2008**, 80, 1005–1012.
- (a) Alonso, F.; Yus, M. *Tetrahedron Lett.* **1996**, 37, 6925–6928; (b) Alonso, F.; Yus, M. *J. Chem. Educ.* **2001**, 78, 1517–1518.
- (a) Alonso, F.; Yus, M. *Adv. Synth. Catal.* **2001**, 343, 188–191; (b) Alonso, F.; Candela, P.; Gómez, C.; Yus, M. *Adv. Synth. Catal.* **2003**, 345, 275–279.
- (a) Alonso, F.; Osante, I.; Yus, M. *Adv. Synth. Catal.* **2006**, 348, 305–308; (b) Alonso, F.; Osante, I.; Yus, M. *Synlett* **2006**, 3017–3020; (c) Alonso, F.; Osante, I.; Yus, M. *Tetrahedron* **2007**, 63, 93–102.
- (a) Alonso, F.; Calvino, J. J.; Osante, I.; Yus, M. *Chem. Lett.* **2005**, 34, 1262–1263; (b) Alonso, F.; Calvino, J. J.; Osante, I.; Yus, M. *J. Exp. Nanosci.* **2006**, 1, 419–433.
- (a) Alonso, F.; Riente, P.; Yus, M. *Synlett* **2007**, 1877–1880; (b) Alonso, F.; Riente, P.; Yus, M. *Eur. J. Org. Chem.* **2008**, 4908–4914; (c) Alonso, F.; Riente, P.; Yus, M. *Tetrahedron* **2008**, 64, 1847–1852; (d) Alonso, F.; Riente, P.; Yus, M. *Tetrahedron Lett.* **2008**, 49, 1939–1942; (e) Alonso, F.; Riente, P.; Yus, M. *Synlett* **2008**, 1289–1292.
- The complete characterisation of the NiNPs has been recently submitted to an specialised catalysis journal.

18. For reviews, see: (a) van der Drift, R. C.; Bouwman, E.; Drent, E. J. *Organomet. Chem.* **2002**, 650, 1–24; (b) Uma, R.; Crévisy, C.; Grée, R. *Chem. Rev.* **2003**, 103, 27–51; (c) Cadierno, V.; Crochet, P.; Gimeno, J. *Synlett* **2008**, 1105–1124.
19. For a review on palladium-catalysed reactions of alcohols, including the isomerisation of unsaturated alcohols, see Muzart, J. *Tetrahedron* **2005**, 61, 9423–9463.
20. See, for instance: (a) Widodo, A. A.; Kato, T.; Butsugan, Y. *Chem. Express* **1993**, 8, 701–704; (b) Shimazu, S.; Baba, N.; Ichikumi, N.; Uematsu, T. J. *Mol. Catal. A: Chem.* **2002**, 182–183, 343–350; (c) Tetrahydrolinalool has been recently obtained as major product (30% conversion) in the 5-ethylriboflavine-catalysed diimide reduction of linalool Smit, C.; Fraaije, M. W.; Minnaard, A. J. J. *Org. Chem.* **2008**, 73, 9482–9485.
21. (a) Olivero, S.; Duñach, E. J. *Chem. Soc., Chem. Commun.* **1995**, 2497–2498; (b) Taniguchi, T.; Ogasawara, K. *Angew. Chem., Int. Ed.* **1998**, 37, 1136–1137; (c) Yasuhara, A.; Kasano, A.; Sakamoto, T. J. *Org. Chem.* **1999**, 64, 4211–4213.
22. Taniguchi, T.; Ogasawara, K. *Tetrahedron Lett.* **1998**, 39, 4679–4682.
23. Wuts, P. G. M.; Greene, T. W. *Greene's Protective Groups in Organic Synthesis*; Wiley-Interscience: Hoboken, 2007, pp 106–109.
24. Asakawa, Y.; Tanikawa, K.; Aratani, T. *Phytochemistry* **1976**, 15, 1057–1059.
25. Alonso, F.; Riente, P.; Yus, M. *Synlett* **2009**, 1579–1582.
26. Alonso, F.; Riente, P.; Yus, M. *Tetrahedron Lett.* **2009**, 50, 3070–3073.